

**AMENDMENTS TO THE SPECIFICATION**

At page 10, please amend the paragraph beginning at line 3 and ending at line 9 as follows:

--One (1) liter of a 1.4% by weight 3,4-polyethylenedioxythiophene/ polystyrene sulfonate dispersion having a weight ratio of the 3,4-polyethylenedioxythiophene to polystyrene-sulfonic acid of 1:8, prepared by evaporating a 3,4-polyethylenedioxythiophene/polystyrene sulfonate dispersion in accordance with Example 2 from EP-A 991 303 (which corresponds to Example 2 of U.S. Patent No. 6,391,481) (U.S. Patent No. 6,391,481 is in the same family as EP-A 991 301)), was homogenized twice using a high-pressure homogenizer at 700 bar and with a nozzle diameter of 0.1 mm.--